

**DESCRIPTION**

Total Thickness	<i>mm</i>	1.00 +/- 0.15
Weight	<i>kg/m<sup>2</sup></i>	1,4 +/-0.2
Density	<i>g/cm<sup>3</sup></i>	1.49
Lenght	<i>mm</i>	3000 +2/+10
Width	<i>mm</i>	1300 0/+4
Stabilization		CaZn

**CLASSIFICATION**

Fire resistance	NFP 92 – 507	M1
	BSI	Class 0
	EN13501-1	Bs2d0
Hygiene and decontamination		Pasteur Sector 4
		bacteriostatic
		Anios compliant
		Bioquell compliant
Decontamination of surface (radionuclide)	ISO 8690	Excellent

**ENVIRONMENT**

TVOC emission	EN 16000-6	<i>after 28 days</i>	< 100 µg/m <sup>3</sup>
---------------	------------	----------------------	-------------------------

**PERFORMANCE**

Impact resistance	ISO 8256	<i>KJ/m<sup>2</sup></i>	443
Impact resistance Charpy +23°C -50% HR	ISO 179-1	<i>KJ/m<sup>2</sup></i>	53,6
Thermal conductivity		<i>W/m<sup>2</sup> °C</i>	6.8
Temperature of bending under load (1.8 N/MM <sup>2</sup> )	ASTM D648	<i>°C</i>	65
Linear coefficient of thermal expansion	D696/79	<i>10-6 K-1</i>	79
Tensile properties at 23°C	ISO 527- 2/1B/50		
Elasticity modulus	50mm/mn	<i>MPA or N/mm<sup>2</sup></i>	2311
Tensile strength		<i>MPA or N/mm<sup>2</sup></i>	29
Elongation at break		<i>in %</i>	41
Welding resistance with Gerflor contract vinyl flooring (wearlayer > 0,5mm)	NF-EN 684	<i>DaN/5cm</i>	>24
Fire propagation			self extinguible

**CHEMICAL AND MARK RESISTANCE**

Hydrochoric acid (HCl)	EN 423	1%	OK
	"	0,5%	OK

Sulfuric acid (H <sub>2</sub> SO <sub>4</sub> )	"	1%	OK
Nitric acid (HNO <sub>3</sub> )	"	1%	OK
Phosphoric acid (H <sub>3</sub> PO <sub>4</sub> )	"	1%	OK
Acetic acid (CH <sub>3</sub> COOH)	"	1%	OK
Hydrogen fluoride (HF)	"	1%	OK
	"	0,5%	OK
Hydrogen peroxide solution (H <sub>2</sub> O <sub>2</sub> )	"	1%	OK
Sodium hydroxide (NaOH)	"	1%	OK
Ammoniac solution (NH <sub>3</sub> )	"	1%	OK
Sodium hudrochlorite (NaClO)	"	1%	OK
	"	0,5%	OK
Methanol (methyl alcohol)	"		OK
Ethanol (ethyl alcohol)	"		OK
Isopropanol (propan-2-ol)	"		OK
Butanol (butyl alcohol)	"		OK
Ethylene glycol	"		OK
Acetone	"		OK
Toluene	"		OK
Trichlorethylene	"		OK
White spirit	"		OK
Heptane	"		OK
Sodium chloride (NaCl)	"	1%	OK
Ammonium fluoride (NH <sub>4</sub> F)	"	1%	OK
Potassium chloride (KCl)	"	1%	OK
Eosine	"		OK
Betadine	"	2%	OK
Iode alcohol	"	2%	OK
Onyx	"		NOK
Javel water	"		OK
Alcohol 70°	"		OK